

Test Report N. 6970 /EL MI

Spett.le
GRANITI FIANDRE S.p.A.
VIA RADICI NORD 112
42014 CASTELLARANO (MO)

Modena 29/12/2015

Receipt N.: 6.970/EL MI	Date of receipt : 20/11/15	Analysis start date: 20/11/15	Analysis end date: 21/12/15
Material:	Ceramics materials		
Product:	Ceramic tile		
Sample:	CALACATTA ACTIVE 300x150 cm Test information: - treated and not-treated specimens : 50 x 50 mm square, 6 mm thickness; - all specimens are rinsed with distilled water and autoclaved at 121°C for 30 minutes before the analysis; - fluorescent UV lamp : mercury-vapor lamp 18 W (PHILIPS PL-L 18W/10/4P); - ultraviolet light radiometer : DELTA OHM model HD2102.2 - serial number 10008472 - model probe : LP471 UVA - UV irradiation intensity : 0.25mW/cm ² - time exposure : 8h - test bacteria : Methicillin-Resistant Staphylococcus aureus ATCC 43300 (MRSA); - inoculated test bacteria suspension : 0.15 ml; - adhesive film : polypropylene film 40 x 40 mm square - transparency rate = 85% for 340-380 nm range; - moisture preservation glass : borosilicate glass 1.1 mm thickness BOROFLOAT SHOTT		
Sampling:	made by customer		
Date of sampling:	20/11/15		

Test	Method	UM	Result
Antibacterial activity photocatalytic materials - S. aureo ATCC 43300*	ISO 27447:2009 - Film adhesion method		
<i>N. bacteria inoculated*</i>		cells/ml	2.200.000
<i>A - average number of bacteria non-treated specimens after inoculation*</i>		cells/ml	320.000
<i>BL - average number of bacteria non-treated specimens after UV irradiation*</i>		cells/ml	130.000
<i>CL - average number of bacteria photocatalytic treated specimens after UV irradiation*</i>		cells/ml	10
<i>RL - photocatalytic antibacterial activity after UV irradiation*</i>		Log10	4,1
<i>Reduction of bacteria from non-treated specimens after UV irradiation*</i>		%	99,99

Test Report N. 6970 /EL MI

Spett.le
GRANITI FIANDRE S.p.A.

Receipt N.: 6.970/EL MI

Date of receipt : 20/11/15

Analysis start date: 20/11/15 Analysis end date: 21/12/15

Test	Method	UM	Result
BD - Average number of bacteria non-treated specimens after dark treatment*		cells/ml	390.000
CD - Average number of bacteria photocatalytic specimens after dark treatment*		cells/ml	360.000
Delta R - photocatalytic antibacterial activity value with UV irradiation*		Log10	4,1

TECHNICAL MANAGER

Dr.ssa Alessandra Carletti
Ordine Nazionale dei Biologi
Albo professionale n. 34638
Sez.A

U: expanded uncertainty associated with single measurement (P = 95 % - K = 2) - LD: Detection limit (the lowest concentration of analyte detectable) - LQ : Limit of Quantification (the lowest concentration of analyte detected with acceptable precision and accuracy) - R% Recovery % . U - R% - LQ - LD are indicated if required by the Customer . PNN : internal method.
Reference standards for microbiological food : ISO 7218:2013 (counting in single dish and two consecutive dilutions) waters : ISO 8199:2005; (results expressed with < 4ufc/ml and < 40ufc / g indicate that microorganisms are present but less than the value expressed ; for values between 4-10 cfu / ml , 4-10 ufc/100ml , 40-100 cfu / g the number of microorganisms is estimated) .
Results of tests with the legal limits are evaluated taking into account the value of the uncertainty and the rules relating to rounding .
Results of tests with the reference values defined by the Customer shall be assessed taking into account the value of the uncertainty only if requested by the Customer. Non-compliant results are given if requested by the Customer.
This Test Report refers only to the sample tested; the name and description of the sample are declared by the Customer . This test report may only be reproduced in full; partial reproduction must be authorized with written approval by the Laboratory . If the test report is digitally signed , the integrity of the document can be confirmed by checking the validity of the digital signature within the file.
REGIONE EMILIA ROMAGNA - AUTORIZZAZIONE AUTOCONTROLLO N° 008/MO/024.